

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification <sup>6</sup> : <b>C07D 473/16, A61K 31/52</b></p>	<p><b>A1</b></p>	<p>(11) International Publication Number: <b>WO 99/20625</b> (43) International Publication Date: 29 April 1999 (29.04.99)</p>
<p>(21) International Application Number: PCT/US98/22451 (22) International Filing Date: 23 October 1998 (23.10.98) (30) Priority Data: 60/063,238 23 October 1997 (23.10.97) US (71) Applicants (for all designated States except US): SMITHK-LINE BEECHAM CORPORATION [US/US]; One Franklin Plaza, Philadelphia, PA 19103 (US). SMITHK-LINE BEECHAM PLC [GB/GB]; New Horizons Court, Brentford, Middlesex TW8 9EP (GB). (72) Inventors; and (75) Inventors/Applicants (for US only): EGGLESTON, Drake [US/GB]; Harlow, Essex (GB). LYNCH, Ian, Robert [GB/GB]; Coldharbour Road, The Pinnacles, Fourth Avenue, Harlow, Essex CM19 5AD (GB). (74) Agents: DINNER, Dara, L. et al.; SmithKline Beecham Corporation, Corporate Intellectual Property, UW2220, 709 Swedeland Road, P.O. Box 1539, King of Prussia, PA 19406-0939 (US).</p>		<p>(81) Designated States: AL, AU, BA, BB, BG, BR, CA, CN, CZ, EE, GE, HU, ID, IL, IS, JP, KP, KR, LC, LK, LR, LT, LV, MG, MK, MN, MX, NO, NZ, PL, RO, SG, SI, SK, SL, TR, TT, UA, US, UZ, VN, YU, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).  Published With international search report.</p>
<p>(54) Title: NOVEL POLYMORPHIC FORMS OF CIPAMFYLLINE</p> <p>(57) Abstract</p> <p>This invention relates to novel crystalline polymorphic forms, Form I, II and IV of Cipamfylline, methods of preparation, and use thereof in the treatment of PDE<sub>4</sub> and TNF mediated diseases. Cipamfylline is 1,3-di-cyclopropylmethyl-8-amino xanthine, and represented by formula (I).</p> <div data-bbox="844 1155 1234 1396"> <p style="text-align: right;">(I)</p> </div>		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

## NOVEL POLYMORPHIC FORMS OF CIPAMFYLLINE

5

## FIELD OF THE INVENTION

This invention relates to novel crystalline polymorphic forms of Cipamfylline, and to methods for preparing them.


10

## BACKGROUND OF THE INVENTION

The capacity to occur in different crystal structures is known as polymorphism and is known to occur in many organic compounds. These different crystalline forms are known as "polymorphic modifications" or "polymorphs" and are realized in their crystalline state. While polymorphic modifications have the same chemical composition, they differ in packing, geometrical arrangement, and other descriptive properties of the crystalline solid state. As such, these modifications may have different solid-state physical properties such as shape, color density, hardness, deformability, stability, and dissolution properties, etc. Polymorphism of an organic drug molecule and its consequences will be appreciated by the skilled artisan.

20

Cipamfylline, 1,3-di-cyclopropylmethyl-8-amino xanthine, has the chemical formula  $C_{13}H_{17}N_5O_2$ , m.w. of 275.31, and the following structural formula:



25

Its synthesis is described in Example 9, in Maschler *et al.*, Great Britain Patent Application No. 8906792.0 filed on March 23, 1989, in its corresponding EPO patent EP 389282, and corresponding US Patent 5,734,051 whose disclosures are incorporated herein by reference in their entirety.

30

Cipamfylline is a PDE<sub>4</sub> inhibitor and is useful in the treatment, including prophylaxis, of disease states mediated thereby.

Cipamfylline was also disclosed to have TNF inhibiting activity in Esser et al., PCT/US91/08734 (also published as EP 558659), and is therefore useful in the treatment, including prophylaxis of TNF mediated disease states. Suitable assays, dosage forms, and dosage ranges, etc. for the polymorphs of this invention for use in the therapeutic treatment of diseases may be found in either the Maschler et al., or the Esser et al. patent applications whose disclosures are incorporated herein by reference in their entirety.

## SUMMARY OF THE INVENTION

10 This invention relates to a novel crystalline polymorph of the 1,3-di-cyclopropylmethyl-8-amino xanthine, referred to hereinafter as Form I, which form of such compound is useful in the treatment of PDE<sub>4</sub> or TNF mediated diseases.

15 This invention also relates to a novel crystalline polymorph of the 1,3-di-cyclopropylmethyl-8-amino xanthine, referred to hereinafter as Form II, which form of such compound is useful in the treatment of PDE<sub>4</sub> or TNF mediated diseases.

20 This invention also relates to a novel crystalline polymorph of the 1,3-di-cyclopropylmethyl-8-amino xanthine, referred to hereinafter as Form IV, which form of such compound is useful in the treatment of PDE<sub>4</sub> or TNF mediated diseases.

## BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 is a characteristic X-ray powder diffraction pattern for Form I. (Vertical axis: Intensity (CPS); Horizontal axis: Diffraction Angle, in Two Theta (degrees)).

25 FIG. 2 is a characteristic X-ray powder diffraction pattern for Form II. (Vertical axis: Intensity (CPS); Horizontal axis: Diffraction Angle, in Two Theta (degrees)).

30 FIG. 3 is a table showing the Torsion Angle Tabulations for Forms II and IV.

FIG. 4 is a Raman spectrum of Form I. (Vertical axis: Intensity; Lower horizontal axis: Wavenumber (cm<sup>-1</sup>)).

35 FIG. 5 is a Raman spectrum of Form II. (Vertical axis: Intensity; Lower horizontal axis: Wavenumber (cm<sup>-1</sup>)).

FIG. 6 is a Raman spectrum of Form IV. (Vertical axis: Intensity; Lower horizontal axis: Wavenumber ( $\text{cm}^{-1}$ )).

5 FIG. 7 is a comparison of the Raman spectra of all three forms, Form I, II and IV, and the carbonyl stretching region of  $1750\text{--}1600\text{ cm}^{-1}$ . (Vertical axis: Intensity; Lower horizontal axis: Wavenumber ( $\text{cm}^{-1}$ )).

10 FIG. 8 is a comparison of the Raman spectra of all three forms, Form I, II and IV, and the region of  $1000\text{--}800\text{ cm}^{-1}$ . (Vertical axis: Intensity; Lower horizontal axis: Wavenumber ( $\text{cm}^{-1}$ )).

15 FIG. 9 is a comparison of the Raman spectra of all three forms, Form I, II and IV, and the region of  $400\text{--}200\text{ cm}^{-1}$ . (Vertical axis: Intensity; Lower horizontal axis: Wavenumber ( $\text{cm}^{-1}$ )).

FIG. 10 depicts the Form I molecule in three dimensions and with a labeling scheme.

FIG. 11 provides for a stereo drawing of the Form I molecule.

20 FIG. 12 shows a Table of Bond Distances in Angstroms for the Form I molecule.

FIG. 13 shows a Table of Bond Angles in Degrees for the Form I molecule.

25 FIG. 14 shows a Table of Torsion Angles in Degrees for the Form I molecule.

FIG. 15 shows a Table of Positional Parameters and Their Estimated Standard Deviations for the Form I molecule. The x, y, and z fractional coordinates indicate the position of atoms relative to the origin of the unit cell, and B(A<sup>2</sup>) is the isotropic temperature factor.

30

FIG. 16 is a characteristic infrared absorption spectrum of a single crystal of Form I.

FIG. 17 is a characteristic infrared absorption spectrum of a single crystal of Form II.

35 FIG. 18 is a characteristic infrared absorption spectrum of a single crystal of Form IV.

FIG. 19 is a comparison of characteristic infrared absorption spectra of the single crystals of Forms I, II and IV.

5 FIG. 20 is a characteristic infrared absorption spectrum in potassium bromide of Form I. (Vertical axis: Transmission (%); Lower horizontal axis: (Wavenumber ( $\text{cm}^{-1}$ )).

10 FIG. 21 is a characteristic infrared absorption spectrum in potassium bromide of Form II. (Vertical axis: Transmission (%); Lower horizontal axis: (Wavenumber ( $\text{cm}^{-1}$ )).

FIG. 22 is a characteristic infrared absorption spectrum of a crushed crystal of Form I.

15 FIG. 23 is a characteristic infrared absorption spectrum of a crushed crystal of Form II.

FIG. 24 is a characteristic infrared absorption spectrum of a crushed crystal of Form IV.

20 FIG. 25 is a comparison of the infrared absorption spectra of a single and crushed crystal of Form IV.

FIG. 26 depicts the Form IV molecule in three dimensions and with a labeling scheme.

25 FIG. 27 provides for a stereo drawing of the Form IV molecule.

FIG. 28 shows a Table of Bond Distances in Angstroms for the Form IV molecule.

FIG. 29 shows a Table of Bond Angles in Degrees for the Form IV molecule.

30 FIG. 30 shows a Table of Torsion Angles in Degrees for the Form IV molecule.

FIG. 31 shows a Table of Positional Parameters and Their Estimated Standard Deviations for the Form IV molecule.

35 FIG. 32 depicts the Form II molecule in three dimensions and with a labeling scheme.

FIG. 33 shows a Table of Bond Distances in Angstroms for the Form II molecule.

FIG. 34 shows a Table of Bond Angles in Degrees for the Form II molecule.

FIG. 35 shows a Table of Torsion Angles in Degrees for the Form II molecule.

FIG. 36 shows a Table of Positional Parameters and Their Estimated Standard Deviations for the Form II molecule.

#### DETAILED DESCRIPTION OF THE INVENTION

It has now been discovered that Cipamfylline can exist as any of several novel crystalline forms, polymorphic forms, which differ from each other in their stability, physical properties, spectral data and methods of preparation. Three of these novel polymorphic forms are described in this application and are hereinafter referred to, respectively, as Form I, Form II, and Form IV.

Of the three novel polymorphs referred to above, Form I, exhibits the greatest stability. Form I is characterized by a minimum of five years crystalline stability.

This invention also relates to a pharmaceutical composition comprising an effective amount of a polymorph of Form I with any of the characteristics noted herein, and a pharmaceutically acceptable carrier or diluent thereof.

This invention also relates to a pharmaceutical composition comprising an effective amount of a polymorph of Form II with any of the characteristics noted herein, and a pharmaceutically acceptable carrier or diluent thereof.

This invention also relates to a pharmaceutical composition comprising an effective amount of a polymorph of Form IV with any of the above characteristics noted herein, and a pharmaceutically acceptable carrier or diluent thereof.

This invention further relates to the use of Form I for the treatment of a PDE<sub>4</sub> or TNF mediated disease in a mammal in need thereof, which method comprises administering to said mammal an effective amount of a polymorph of Form I with any of the characteristics noted herein.

This invention further relates to the use of Form II for the treatment of a PDE<sub>4</sub> or TNF mediated disease in a mammal in need thereof, which method comprises administering to said mammal an effective amount of a polymorph of Form II with any of the characteristics noted herein.

This invention further relates to the use of Form IV for the treatment of a PDE<sub>4</sub> or TNF mediated disease in a mammal in need thereof, which method comprises administering to said mammal an effective amount of a polymorph of Form IV with any of the characteristics noted herein.

This invention results from a determination that certain batches of Cipamfylline showed differences in their IR mull spectra. All batches were prepared by the same route with ethanol as the final recrystallization solvent therefore it appeared possible that speed of crystallization may affect crystal form. In the light of this, recrystallized samples were prepared by crash cooling a portion of the hot liquid while the remainder was allowed to stand and crystallize unaided. In each case batch size was ca. 1g or less. Samples were dried over silica gel under vacuum at room temperature. In this recrystallization program, three polymorphic forms have been positively identified, and are described herein as Forms I, II and IV.

Therefore, this invention also relates to a method of preparing a polymorph of Form I with any of the above characteristics comprising crystallizing Cipamfylline in an alcoholic solution of ethanol (s/f), propanol(s/f), butanol(s/f), isopropanol(s/f), or an organic solvent of ethyl acetate(s/f), toluene\*, or as a solvent, water\*. Under certain conditions, tetrahydrofuran (s/f), and acetone (s) may also be used.

In additional work with fast cooling, i.e. an ice water bath for use with small scale samples, the time for the reaction temperature to drop from reflux to ambient takes approximately 1 minute with ethanol as a solvent.

In a preferred embodiment of this invention, 1-propanol is the solvent of choice to prepare Form I polymorphic forms.

This invention also relates to a method of preparing a polymorph of Form II with any of the above characteristics comprising crystallizing Cipamfylline in an alcoholic solution of methanol(s/f), or an organic solvent of tetrahydrofuran (s), or acetone (f). Under certain conditions, chloroform\* or pyridine\* may be used.

This invention also relates to a method of preparing a polymorph of Form IV with any of the above characteristics comprising crystallizing Cipamfylline in an organic solvent of 50:50 mixture of ethanol and isopropanol.

\*Due to the particularly low solubility of Cipamfylline in solvent marked with an asterix (\*), such as toluene or water for Form I, the recrystallization procedure was modified, i.e. the hot solution was filtered to remove undissolved material and the filtrate was allowed to stand and crystallize out the compound.

The (s) term as used herein refers to slow, ambient recrystallization. It is noted that the term "slow" cooling (and "fast" cooling) are relative terms. In this particular meaning slow cooling may involve removal of the oil bath and air cooling.



On the basis of scale alone (approximately 1 gm quantities for some experiments, versus a commercial batch size) cooling may actually be quite fast, such as in the 15 to 30 minute range. However, under controlled circumstances, slow cooling is generally defined as approximately one (1) hour from reflux to ambient temperature. 5 Very slow cooling will be approximately from about four (4) hours from reflux to ambient. Under these conditions Form II may also be obtained from ethanol as described later in this document. However, similarly under the small batch sizes in some of the experiments used for Form I, the ethanol (slow cooling) route is not necessarily a reliable solvent/temperature of choice for Form I. It is also noted that 10 with regard to the use of acetone in fast cooling (i.e. use of an ice bath), Form I is formed. Limited analysis also indicates that use of acetone under the fast cooling route is not necessarily a reliable solvent/temperature of choice for Form II.

The (f) term as used herein refers to fast, crash cool recrystallization, such as 15 by placing the flask in a ice water bath, or similar techniques for larger scale processing.

These three novel crystalline polymorphs of Cipamfylline, also referred to as BRL 61063, all melt at about 305° C. to about 313° C. 20

The crystalline polymorph, Form I, exhibits a characteristic X-ray powder diffraction pattern with characteristic peaks expressed d spacing (Å) in decreasing intensity, at 12.302, 7.702, 8.532, 4.289, and 2.854 as depicted in FIG. 1. A discussion of the theory of X-ray powder diffraction patterns can be found in Stout & 25 Jensen, X-Ray Structure Determination; A Practical Guide, Mac Millian Co., New York, N.Y. (1968).

The crystalline polymorph, Form II, exhibits a characteristic X-ray powder diffraction pattern with characteristic peaks expressed d spacing (Å) in decreasing 30 intensity, at 12.001, 6.702, 3.687, 3.773, and 7.345 as depicted in FIG. 2.

This invention also relates to the crystalline polymorph Forms I, II, and IV, of Cipamfylline that are further characterized by the crystal parameters obtained from single crystal X-ray crystallographic analysis as set forth in Tables 1, 2 and 3 below. 35 The 3-D X-ray data was collected at ambient temperatures.

TABLE I

## Crystal Parameters of Form I

	Crystal Shape (mm):	Flat needles
	Crystal Dimensions:	1.0 x 0.12 x 0.08 mm
5	Crystal Color:	Colorless
	Space Group:	P1 triclinic #2
	Temperature:	295K
	Cell Constants:	a = 10.829 (2) Å
		b = 12.636(2) Å
10		c = 5.105(3) Å
		alpha ( $\alpha$ ) = 99.48(4)
		beta ( $\beta$ ) = 91.53(4)
		gamma ( $\gamma$ ) = 83.84(3)
	Volume:	685.0(8) Å <sup>3</sup>
15	Molecules/unit cell (Z)	4
	$\rho$ (calc), Density	1.354 g/cm <sup>-3</sup>
	$\mu$	7.362 cm <sup>-1</sup>
	F(000)	292

20

TABLE II

## Crystal Parameters of Form II

	Crystal Shape (mm):	Rectangular blocks
	Crystal Colour:	Colorless
25	Crystal Dimensions:	0.80 x 0.50 x 0.15 mm
	Space Group	P2 <sub>1</sub> /c monoclinic #14
	Cell Constants	a = 12.227 (4) Å
		b = 7.448(2) Å
		c = 14.946 (8) Å
30		alpha ( $\alpha$ ) = 90 (4)
		beta ( $\beta$ ) = 97.95(4)
		gamma ( $\gamma$ ) = 90(4)
	Volume	1348.1(9) Å <sup>3</sup>
	Molecules/unit cell (Z)	4
35	$\rho$ (calc) Density	1.356 g/cm <sup>-3</sup>
	$\mu$	0.896 cm <sup>-1</sup>
	F(000)	584

TABLE III

## Crystal Parameters of Form IV

	Crystal Shape (mm)	Flat needles
5	Crystal Color	Colorless
	Crystal Dimensions	0.60 x 0.10 x 0.05 mm
	Space Group	P1 triclinic #2
	Temperature	295K
	Cell Constants	a = 10.210(3) Å
10		b = 13.753(2) Å
		c = 4.942(31) Å
		alpha (α) = 97.94(2)
		beta (β) = 97.95(4)
		gamma (γ) = 83.33(2)
15	Volume	677.1(5) Å <sup>3</sup>
	Molecules/unit cell (Z)	2
	ρ (calc) Density	1.350 g/cm <sup>-3</sup>
	μ	7.448 cm <sup>-1</sup>
	F(000)	292

20

The unit cell dimension is defined by three parameters; length of the sides of the cell, relative angles of sides to each other and the volume of the cell. The lengths of the sides of the unit cell are defined by a, b and c. The relative angles of the cell sides are defined by alpha, beta, and gamma. The volume of the cell is defined as V.

25 A more detailed account of unit cells can be found in Chapter 3 of Stout & Jensen, X-Ray Structure Determination; A Practical Guide, Mac Millian Co., New York, N.Y. (1968).

30 The crystalline state of a compound can be unambiguously described by several crystallographic parameters: unit cell dimensions, space group, and atomic position of all atoms in the compound relative to the origin of its unit cell. These parameters are experimentally determined by single crystal X-ray analysis. It is possible for a compound to form more than one type of crystal. These different crystalline forms are called polymorphs. It has now been discovered that there are

35 three polymorphic forms of Cipamfylline. This discovery was confirmed by three separate single crystal X-ray analysis. A comparison of the unit cell dimensions and space groups of these three crystalline states are shown in Tables 1 to 3 above.

Plotting the atomic positions, for the three polymorphs, of the atoms derived from the single crystal X-ray analysis confirms that the crystals contain Cipamfylline and no other molecules of crystallization or impurity.

5 Figure 10 depicts the molecule in three dimensions and with a labeling scheme. Figure 11 provides for a stereo drawing. Overall, the molecular conformation observed in Form I is identical to that of Form IV, with the exception of a clear disorder in one of the cyclopropyl groups (atoms C12 and C13), which was modeled with two positions of equal occupancy for each of these atoms. The high  
10 degree of thermal motion in the other cyclopropyl group (atoms C16 and C17) suggests that it may be experiencing conformational flexing.

The unit cell of Form I crystals is of the same form as that of Form III, with similar cell dimensions, a volume of 8 Å<sup>3</sup> larger, and correspondingly, a density  
15 reduced by 0.15g cm<sup>-3</sup>. All of these effects are in keeping with the presence of disorder in the channel which the cyclopropyl groups occupy.

Hydrogen bonding in this crystal structure is all intermolecular in nature and is similar, in terms of specific interactions to that seen in Form IV. As in the Form IV  
20 structure, the positions of the amino hydrogens are indicated from difference Fourier electron density maps. The position of H2N2 is not consistent with the participation of that hydrogen in a hydrogen bonding interaction. A distance of 3.399(3)Å between atoms N2 and O5 in Form I, however, suggest the possibility of a weak interaction analogous to that observed in Form II structure, although the distance  
25 observed in this form is longer by 0.4 Angstroms. When a position for H(2)N(2) was calculated which would satisfy this hydrogen bonding interaction, and attempts were made to refine it, the thermal value became unreasonable large, suggesting that the data do not support this alternative position. Thus the refinement was completed with H2N2 in its original location as indicated by difference Fourier synthesis. The  
30 associated metrical details of the other two hydrogen bond are:

<i>H-bonding atoms</i>	<i>Atom-atom distance</i>	<i>Angle</i>
N(2)-----N(1)	3.067(3) Å	173(3) °
H(1)N(2)-----N(1)	2.16(3) Å	
N(3)-----O(5)	2.793(3) Å	165(4) °
HN(3)-----O(5)	2.02(3) Å	

*Summary of hydrogen-bonding of Form I*

With regard to Form IV, Figure 26 depicts the molecule in three dimensions and with a labeling scheme. Figure 27 provides for a stereo drawing of Form IV. For the data described in this section, crystals of Form IV were grown from a 50/50 mixture of ethanol and isopropanol by slow evaporation. Further, crystals of Form II were also grown from this solvent mixture with Form II crystals appearing to nucleate first, with needles of Form IV coming after the solution has evaporated for several days. Overall the molecular conformation observed in Form IV is very similar to that of Form II. Principal differences are concentrated in the rotational orientation of the cyclopropyl groups which display a nearly enantiomorphous relationship to their counterparts in the Form II structure, as summarized in the torsion angle tabulation Table 4, and shown in Figure 3 herein.

Hydrogen bonding in the crystal structure for Form IV is all intermolecular in nature and is similar, in terms of specific interactions to that seen in Form II. A major difference involves one of the two hydrogens on N2. There is a clear indication of the position for H1N2 in difference difference Fourier electron density maps. The position is not consistent with the participation of that hydrogen in a hydrogen bonding interaction. A distance of 3.273(3)Å between atoms N2 and O5 in Form IV, however, suggest the possibility of a hydrogen bonding interaction analogous to that observed in Form II structure, although the distance observed in this form is longer by 0.2Å. When a position for H1N2 was calculated which would satisfy this hydrogen bonding interaction, and attempts were made to refine it, the thermal value became unreasonable large, suggesting that the data do not support this alternative position. Thus the refinement was completed with H1N2 in its original location as indicated by difference Fourier synthesis. The associated metrical details of the other two hydrogen bond are:

<i>H-bonding atoms</i>	<i>Atom-atom distance</i>	<i>Angle</i>
N(2)-----N(1)	3.042(2) Å	173(2) °
H(1)N(2)-----N(1)	2.10(2) Å	
N(3)-----O(5)	2.731(2) Å	160(2) °
HN(3)-----O(5)	1.91(2) Å	

*Summary of the hydrogen bonding of Form IV*

With regard to Form II, Figure 32 depicts the Form II molecule in three dimensions and with a labeling scheme. The hydrogen bonding for the crystal structure of polymorph Form II, is all intermolecular in nature. The associated meterical details are:

5

<i>H-bonding atoms</i>	<i>Atom-atom distance</i>	<i>Angle</i>
N2 -----O5 H1N2----O5	3.049(3)Å 2.26(3)Å	Angle 151(2)°
N2-----N1 H2N2----N1	3.071(3)Å 2.41(3)Å	Angle 137(3)°
N3-----O5 HN3----O5	2.741(3)Å 1.90(3)Å	Angle 168(2)°

*Summary of the hydrogen bonding of Form II*

This structural information clearly shows that Forms I, II, and IV of Cipamfylline are all crystallographically different. The hydrogen bonding in all the forms is intermolecular in nature, and all three possess hydrogen bonding between HN(2)-----N(1) and HN(3)-----O(5).

10

#### **Experimental Details:**

##### Form I:

Flat needles were grown by slow evaporation from a mixture of ethyl acetate and butanol. Lattice parameters were determined from the setting angles of 25 reflections well distributed in reciprocal space measured on an Enraf Nonius CAD-4 diffractometer, and are further described in Table 5 below. A full sphere of intensity data also were collected on the diffractometer using graphite monochromated copper radiation from a rotating anode source and an  $\omega$ -2 $\theta$  variable speed scan technique. Intensities of three monitor reflections measured at the beginning, end and every two hours of exposure time changed by at most +/- 0.1%. Three orientation controls also were monitored to assess any crystal movement during the experiment. Data were corrected for Lorentz and polarization effects, and using the DIFABS algorithm, for the effects of absorption. Redundant observations were averaged to obtain the final data set.

25

The structure was solved by direct methods using the SHELXS program series. Atomic positions were initially refined with isotropic temperature factors and subsequently with anisotropic displacement parameters. The function minimized was

$\sum w(|F_o| - |F_c|)^2$ . Weights,  $w$ , were eventually assigned to the data as  $w = 1/\sigma^2(f_o) = \{\sigma^2(I_c) + (0.04I)^2\}$ . Positions for the hydrogen atoms attached to nitrogens were discovered in subsequent difference Fourier maps. Positions for hydrogen atoms attached to carbons were calculated based on geometrical considerations and held fixed in the final refinement stages along with isotropic temperature factors assigned 1.3(Beq) of the attached atom. Hydrogen atoms on the cyclopropyl groups were omitted from the refinement. All other hydrogen positions were refined along with isotropic temperature factors. The full matrix least-squares refinement converged ( $\max \Delta/\sigma = 0.05$ ) to values of the conventional crystallographic residuals  $R = 0.056$ ,  $wR = 0.092$ . A final difference Fourier map was featureless with maximum density of  $\pm 0.285 \text{ e}\text{\AA}^{-3}$ . Values of the neutral atom scattering factors were taken from the International Tables for X-ray Crystallography.

Table 5  
Intensity Measurement Data for Form I

	Diffractometer:	Enraf Nonius CAD4
5	Radiation:	CuK $\alpha$ $\lambda$ = 1.5406Å
	Monochromator:	Graphite Single Crystal
	Scan Technique	$\omega$ -2 $\theta$ scan
	Scan Speed:	Variable 1.50 to 6.7 deg min <sup>-1</sup> in $\omega$
	Background Measurements	Moving crystal-moving counter at each end of the
10		scan range; scan time/background time = 2.0
	Range of Data:	2° ≤ 2 $\theta$ ≤ 60°
		-12 ≤ h ≤ 12
		-14 ≤ k ≤ 14
		-5 ≤ l ≤ 5
15	Standard Reflections:	Three standards measured every three hours of x-ray exposure time
	Total No. Reflections;	2320
		2032 unique
	Rint:	1.2%
20	No. of Observed Data	1749 I > 3 $\sigma$ (I)
	No. of Variables:	199
	p:	0.04
	R:	0.056%
	Rw:	0.092%
25	Goodness of Fit:	3.311
	Absorption Correction:	0.868 min 1.254 max 0.991 ave

30 The complete single crystal X-ray experimental data used to produce the structure displayed in FIG. 10 for Form I is included in Figures 12 to 15. The parameters presented in the tables are measured in units commonly used by those skilled in the art. A more detailed discussion of the units of measure can be found in International Tables for X-ray Crystallography, Vol. IV, pp. 55, 99, 149 Birmingham: Kynoch Press, 1974, and G. M. Sheldrick, SHELXTL. User Manual, Nicolet Instrument Co., 1981.

35



Form II:

Rectangular plates were grown by slow evaporation from a solution prepared in methanol/2-butanone. Lattice parameters were determined from the setting angles of 25 reflections well distributed in reciprocal space measured on an Enraf Nonius  
5 CAD-4 diffractometer, and further described in Table 6. Intensity data also were collected on the diffractometer using graphite monochromated molybdenum radiation and an  $\omega$ -2 $\theta$  variable speed scan technique. A correction was applied to the data for a 4.8% decrease in the intensities of three monitor reflections measured at the beginning, end and every two hours of exposure time. Three orientation controls  
10 also were monitored to assess any crystal movement during the experiment. Data were corrected for Lorentz and polarization effects, and using the DIFABS algorithm, for the effects of absorption. Symmetry equivalents and zonal reflections were averaged to obtain the final data set.

15 The structure was solved by direct methods using the MULTAN80 program series. Atomic positions were initially refined with isotropic temperature factors and subsequently with anisotropic displacement parameters. The function minimized was  $\sum w(|F_o| - |F_c|)^2$ . Weights,  $w$ , were eventually assigned to the data as  $w = 1/\sigma^2(f_o) = [\sigma^2(I_c) + (0.04I)^2]$ . Positions for the hydrogen atoms were  
20 discovered in subsequent difference Fourier maps. The positions and isotropic temperature factors for amino hydrogen atoms and the methine hydrogens on the cyclopropyl rings were allowed to refine. Positions for all other hydrogen atoms were calculated based on geometrical considerations and held fixed in the final refinement stages along with isotropic temperature factors assigned 1.3(Beq) of the  
25 attached atom. The full matrix least-squares refinement converged ( $\max \Delta/\sigma = 0.005$ ) to values of the conventional crystallographic residuals  $R = 0.044$ ,  $wR = 0.054$ . A final difference Fourier map was featureless with maximum density of  $\pm 0.196 \text{ e}\text{\AA}^{-3}$ . Values of the neutral atom scattering factors were taken from the International Tables for X-ray Crystallography.

30

The complete single crystal X-ray experimental data used to produce the structure displayed in FIG. 32 for Form II is included in Figures 33 to 36. The parameters presented in the tables are measured in units commonly used by those skilled in the art.

Table 6  
Intensity Measurement Data for Form II

	Diffractometer:	Enraf Nonius CAD4
5	Radiation:	MoK $\alpha$ $\lambda = 0.71073 \text{ \AA}$
	Monochromator:	Graphite Single Crystal
	Scan Technique	$\omega$ -2 $\theta$ scan
	Scan Speed:	Variable 2.50 to 6.7 deg min <sup>-1</sup> in $\omega$
10	Background Measurements	Moving crystal-moving counter at each end of the scan range; scan time/background time = 2.0
	Range of Data:	$2^\circ \leq 2\theta \leq 60^\circ$ $0 \leq h \leq 14$ $0 \leq k \leq 8$ $-17 \leq l \leq 17$
15	Standard Reflections:	Three standards measured every three hours of x-ray exposure time
	Total No. Reflections:	2469 2353 unique
	Rint:	3.4 %
20	No. of Observed Data:	1417 $I > 3 \sigma(I)$
	No. of Variables:	202
	p:	0.04
	R:	0.044%
	Rw:	0.054%
25	Goodness of Fit:	1.403
	Extinction Coefficient:	$7.869(1) \times 10^{-7}$
	Decay Correction:	0.9769 min, 1.1374 max

Form IV:

- 30 Flat needles were grown by slow evaporation from a 50/50 mixture of ethanol and isopropanol. Lattice parameters were determined from the setting angles of 25 reflections well distributed in reciprocal space measured on an Enraf Nonius CAD-4 diffractometer, and further described in Table 7. A full sphere of intensity data also were collected on the diffractometer using graphite monochromated copper radiation
- 35 from a rotating anode source and an  $\omega$ -2 $\theta$  variable speed scan technique. Intensities of three monitor reflections measured at the beginning, end and every two hours of exposure time changed by at most +/- 1.1%. Three orientation controls also were

monitored to assess any crystal movement during the experiment. Data were corrected for Lorentz and polarization effects, and using the DIFABS algorithm, for the effects of absorption. Symmetry equivalents and Friedel related mates were averaged to obtain the final data set.

5

The structure was solved by direct methods using the SHELXS program series. Atomic positions were initially refined with isotropic temperature factors and subsequently with anisotropic displacement parameters. The function minimized was  $\sum w(|F_o| - |F_c|)^2$ . Weights,  $w$ , were eventually assigned to the data as  $w = 1/\sigma^2(F_o) = [\sigma^2(I_c) + (0.04I)^2]$ . Positions for the hydrogen atoms attached to nitrogens were discovered in subsequent difference Fourier maps. Positions for hydrogen atoms attached to cyclopropyl methylene carbons were calculated based on geometrical considerations and held fixed in the final refinement stages along with isotropic temperature factors assigned 1.3(Beq) of the attached atom. All other hydrogen positions were refined along with isotropic temperature factors. The full matrix least-squares refinement converged ( $\max \Delta/\sigma = 0.01$ ) to values of the conventional crystallographic residuals  $R = 0.049$ ,  $wR = 0.071$ . A final difference Fourier map was featureless with maximum density of  $\pm 0.515 \text{ e}\text{\AA}^{-3}$ . Values of the neutral atom scattering factors were taken from the International Tables for X-ray Crystallography.

10

15

20

Table 7  
Intensity Measurement Data for Form IV

	Diffractometer:	Enraf Nonius CAD4
5	Radiation:	CuK $\alpha$ $\lambda$ = 1,5406Å
	Monochromator:	Graphite Single Crystal
	Scan Technique	$\omega$ -2 $\theta$ scan
	Scan Speed:	Variable 2.50 to 6.7 deg min <sup>-1</sup> in $\omega$
	Background Measurements	Moving crystal-moving counter at each end of the
10		scan range; scan time/background time = 2.0
	Range of Data:	2° ≤ 2 $\theta$ ≤ 60°
		-11 ≤ h ≤ 11
		-15 ≤ k ≤ 15
		-5 ≤ l ≤ 5
15	Standard Reflections:	Three standards measured every three hours of x-ray exposure time
	Total No. Reflections;	3998
		2017 unique
	Rint:	2.5%
20	No. of Observed Data	1662 I > 3 $\sigma$ (I)
	No. of Variables:	202
	p:	0.04
	R:	0.049%
	Rw:	0.071%
25	Goodness of Fit:	2.095
	Extinction Coefficient:	1.411(1) × 10 <sup>-6</sup>
	Absorption Correction:	0.911 min 1.088 max 0.997 ave

30 The complete single crystal X-ray experimental data used to produce the structure displayed in FIG. 26 and 27, for Form IV is included in Figures 28 to 31. The parameters presented in the tables are measured in units commonly used by those skilled in the art.

35 The results of a single crystal X-ray analysis are limited to, as the name implies, the one crystal placed in the X-ray beam. Crystallographic data on a large group of crystals provides powder X-ray diffraction. If the powder is a pure crystalline compound a simple powder diagram is obtained. To compare the results

of a single crystal analysis and powder X-ray analysis a simple calculation can be done converting the single crystal data into a powder X-ray diagram, SHELXTL Plus (trademark) computer program, Reference Manual by Siemens Analytical X-ray Instrument, Chapter 10, p. 179-181, 1990. This conversion is possible because the single crystal experiment routinely determines the unit cell dimensions, space group, and atomic positions. These parameters provide a basis to calculate a perfect powder pattern. Comparing this calculated powder pattern and the powder pattern experimentally obtained from a large collection of crystals will confirm if the results of the two techniques are the same.

#### X-ray powder diffraction (XRD)

X-ray powder diffraction showed differences between all three forms of polymorphs. Analysis on 4 x Form I samples and 4 x Form II samples showed that consistent matching diffraction patterns were obtained for each set. This data is presented in Figures 1 and 2 herein.

#### Infrared Spectroscopy (IR)

The infrared absorption spectra has positively identified the existence of Forms I, II and IV. This data is presented in Figures 16 to 25 for compound, single crystal and crushed crystals of the various polymorphic forms.

In a compression and grinding study Form I was shown to be stable to compression and grinding, while Form II was shown to be stable to compression but not to severe grinding.

Comparison of the IR spectra of Forms I and IV shows notable differences. The prominent band in a putative methylene deformation region at  $1430\text{ cm}^{-1}$  (with a shoulder at  $1442\text{ cm}^{-1}$ ) for Form I is split in Form IV to give a band at  $1424\text{ cm}^{-1}$  (with a shoulder at  $1434\text{ cm}^{-1}$ ) and a band at  $1455\text{ cm}^{-1}$  (with a shoulder at  $1466\text{ cm}^{-1}$ ). The carbonyl stretching bands in Form I occur at  $1648\text{ cm}^{-1}$  (with a shoulder at  $1656\text{ cm}^{-1}$ ) and  $1682\text{ cm}^{-1}$ , whereas Form IV they occur at  $1656\text{ cm}^{-1}$  and  $1694\text{ cm}^{-1}$ . Weak features in the Form IV spectra at roughly  $2000$  and  $2300\text{ cm}^{-1}$  are absent in Form I, but these may represent overtones from the carbonyl region.

These spectra were recorded using a Spectra-Tech Plan II microscope coupled to a P-E 1760 FTIR spectrometer (64-256 scans, ratio mode, MCT detector,  $4\text{ cm}^{-1}$  resolution, dry air purge). Spectra of samples without sample preparation were obtained by mounting crystals on a diamond window. Crushed crystals were

prepared using a Spectra-Tech micro-Sample Plan (a compression cell) fitted with diamond windows. A stereo microscope was used to observe the behavior of the crystals during compression. After compression, the diamond windows were separated and a spectrum was recorded of the material adhering to one of the windows.

IR spectra of single crystals of Forms I, II and IV show numerous differences as well and are readily distinguishable. There are significant differences in relative band intensities between the IR spectra of single crystals of Forms I and II and the corresponding spectra obtained from potassium bromide discs; these differences occur throughout the spectra, but are most obvious below 1700cm<sup>-1</sup>. In particular, note the difference in relative intensities of the bands near 1530, 1440, 1260, and 800 cm<sup>-1</sup> in the spectra of Form I, and the bands near 1540, 1420, 1260 and 1060 cm<sup>-1</sup> in the spectra of Form II.

The spectra of crushed crystals are very similar to the corresponding KBr disc spectra. This is not surprising since both crushed crystals and KBr discs represent all molecular orientations. In many cases adequate IR transmission through crystalline samples can only be achieved by crushing.

There is poor correspondence between the single crystal and crushed crystal spectra of Form IV, with the most marked difference occurring in the regions 1660-1620, 1260-1180, 1000-920, and 800 -750 cm<sup>-1</sup>. However the crushed crystal spectra of Form IV are very similar to the crushed crystal spectra of Form I. For these IR spectra, Form IV crystals were obtained in the presence of those of form II, by slow evaporation from 50:50 ethanol: isopropanol and separated by hand. Conversion of Form IV to Form I is perhaps not surprising; three dimensional X-ray diffraction data indicates that molecular conformation (aside from orientation in the cyclopropyl groups) and hydrogen-bonding (in terms of specific interactions) are similar in Forms I and IV. In forms I and IV only one of the amino hydrogens is involved in hydrogen-bonding (this contrasts with Form II, in which all hydrogen donors were found to be involved). These findings relate well to the conclusions drawn from the single crystal infrared spectra of the three forms, where the N-H stretching regions of Forms I and IV are similar, and different to Form II. Forms I and IV each have a band near 3455 cm<sup>-1</sup> which is assigned to an unassociated NH function. In Form II this band is absent and it is clear that all hydrogen donors are involved in hydrogen-bonding.

IR spectra of single crystals of Form IV have been recorded on different instruments and are similar, except in the region of  $1280\text{-}1260\text{cm}^{-1}$ . This can be explained by orientation effects. A definitive spectra of Form IV is presented herein as Figure 18.

#### RAMAN Spectra

Raman Spectra for Forms I, II and IV are also shown herein as Figures 4 to 9. As can clearly be seen, significant differences exist between the spectra of the three forms, allowing them to be readily distinguished.

Form IV, under pressure has been shown under some circumstances to convert to Form I, therefore, conventional sampling techniques, such as alkali halide discs, or Nujol mull, may not be the best way to obtain infrared spectra for this polymorph as the time involved in selecting appropriate sized crystals and obtaining a good quality spectra is high.

Raman spectroscopy provides for a quick method of distinguishing Forms I, II and IV from each other without the need for sample preparation.

Spectra were recorded using a Perkin-Elmer 2000 FT-Raman spectrometer equipped with an Nd:YAG NIR laser ( $1.064\mu\text{m}$ ). The scanning conditions were 64-256 scans, quartz beamsplitter,  $4\text{cm}^{-1}$  resolution and 1W laser power. The spectra of Form IV (Figure 6) shows a significant amount of Raman scatter from the glass vial. This is seen as an underlying curve with a broad maximum near  $400\text{cm}^{-1}$ . Glass makes only a minor contribution to the relatively intense spectra of Forms I and II (Figures 4 and 5).

The Raman spectra of Forms I, II and IV show numerous differences and are readily distinguishable. The carbonyl stretching region,  $1750\text{-}1600\text{cm}^{-1}$  (Figure 7) shows the most marked difference between the forms (as was found to be the case with the IR spectra recorded from single crystals (shown herein as Figures 16 to 18). Significant difference exist between the three forms over the range of  $1000\text{-}800\text{cm}^{-1}$  (Figure 8). The region  $400\text{-}200\text{cm}^{-1}$  (inaccessible when recording spectra using an infrared microscope) also shows significant differences (Figure 9), though sensitivity in this region is relatively poor due to detector response.

#### Heats of Solution

Heats of solution were determined using acetone and methanol as suitable solvents. The endothermic values are given in Table 8 below. Different polymorphic forms give rise to different heats of solution. This is demonstrated by the data obtained herein. The value of  $H_T$ , the heat of transition, is equal to the difference in

crystal lattice energy of the two forms and is the same in both solvents. This is predicted since individual enthalpies are solvent dependent but difference are not. From these results it suggests that dissolution of Form II is more endothermic in both solvents and therefore the more stable form. Heats of solution for Form IV are in progress.

Table 8

Form	Methanol (kcal/mol)	Acetone (kcal/mol)
1	4.81	3.93
2	6.47	5.59
$\Delta H_T$	1.66	1.66

#### Thermal Analysis

Differential Scanning Calorimetry (DSC) could not differentiate the three forms of Cipamfylline. In each case thermograms showed melting only with similar onset and peak temperatures, typically  $T_e$  312,  $T_p$  314°C. However, when the heating rate was reduced sufficiently, the melting endotherm appeared as a fused melt, i.e. two components melting. This behavior was common to both Forms I and II.

Thermomicroscopic observations showed that all three forms sublime. The onset of sublimation was different for each form and continued over a wide temperature range (130 - 290°C on a non-calibrated instrument). This is not evident on the DSC thermograms. Melting occurred over a range (310-323°C on a non-calibrated instrument) for all three forms. The possibility of two components melting consecutively could not be distinguished. The sublimate was collected for all three forms and analyzed by IR and NMR. This showed that Form I had been produced.

Forms I, and II were annealed and were found to have converted to Form I by IR. The annealing procedure consisted of heating at 10°C/min from ambient to ca. 250°C and holding at this point for 1/2 - 1 hour, then allowing the sample to cool slowly to room temperature.

The above thermal experiments appear to indicate that Form I is the most stable form. This could explain the similarity in melting points of the three forms.



**Synthetic Methods of Recrystallization:**

Various batches of Cipamfylline were prepared by the same route and the final recrystallization solvent and rate of cooling were varied as shown in Table 9 below.

5

Table 9

Solvent	Rate of Cooling	Recovery	Polymorph produced
Ethanol	slow	75 %	Form II
Ethanol	very slow	75 %	Form II
Methanol	slow	70 %	Form II
Acetone	fast	22 %	Form I
Tetrahydrofuran	fast	33 %	Forms I and III*
Tetrahydrofuran	slow	58 %	Form I

10 \*In the case of THF (fast), it appears that the Form I produced is contaminated with another form, Form III. All data indicates that Form III could be a polymorph, but has not been characterised as it always seems to be produced in mixtures. Slow cooling in this solvent produced Form I.

**Form II recrystallization:**

15 Another experimental procedure used to recrystallize Form II from a solvent mixture of methanol/2-butanone as follows:  
Solid material from a cipamfylline sample was added to an aliquot of 2-butanone in a glass vial and warmed gently on a hot plate with stirring. Methanol was added drop-wise to the stirring warm solution until all solid material appeared to  
20 have dissolved. Small holes were placed in the plastic vial cap and the clear, colorless solution was left to evaporate slowly in a hood at ambient temperature. Rectangular crystals of Form II appeared within 11 days.

25 In yet another study, Cipamfylline (1g) was dissolved in EtOH (55 volumes) and cooled the solutions to 20-25°C over 1 hour and 4 hours respectively. The results are shown in Table 10 below.

Table 10 Recrystallisation of Cipamfylline from EtOH

Examp le	scale (mmol )	time to cool <sup>a</sup> to 20-25°C (h)	recovered yield (%)	polymorphi c <sup>b</sup> form
1	3.6	1	74.9	II
2	3.6	4	75.2	II

notes: a Time to cool from reflux (~78°C) to about 20-25°C.

b Determined by IR Spectroscopy

- 5 In both cases , cooling over a prolonged period ( $\geq 1$ h) gave Cipamfylline in polymorphic form II.

Form IV recrystallization:

- 10 In another experimental procedure for recrystallization of Form IV, solid material from sample a Cipamfylline sample was added to an aliquot of isopropanol in a glass vial and warmed gently on a hot plate with stirring. An equal volume of ethanol was added and stirring continued until all solid material appeared to have dissolved. Small holes were placed in the plastic vial cap and the clear solution was left to evaporate slowly in a hood at ambient temperature. Over a short time
- 15 rectangular crystals of Form II appeared followed in several days by needles, one of which was used for the structure determination of Form IV.

Form I recrystallization:

- 20 In another experimental procedure for purification of Cipamfylline, (15.5g) was dissolved in n-propanol (300 mL) at reflux. Cooling to room temperture lead to precipitation of a purified product, of Form I which was isolated by filtration and dried at 70 °C overnight. Wt. recovered Cipamfylline = 11.96g; Yield = 63%. Alternative solvents, such as n-propanol/water, 3:1 also lead to similar yields and results.

25

As noted above, 1-Propanol is a preferred solvent to prepare Cipamfylline in polymorphic form I. The recrystallization procedure with 1-propanol has been carried out on larger scale, approx. 2 kg scale with repeated success.

Cooling times from 97 °C to ambient temperature have varied from about 70 minutes to overnight (approx. 8 to 12 hours). Form I has been formed reproducibly.

5 This process can be summarised below:

Crude BRL-61063 (2.06 kg) was dissolved in 1-propanol (40 L) at about 97 °C. The reaction was then cooled to about 18 °C over about 70 minutes. The resulting suspension was filtered, the solid washed with prechilled 1-propanol (3 x 0.6 L) and dried in air at about 50 °C overnight to give purified Cipamfylline  
10 (1.85 kg, 90 %) Form I product.

In yet another recrystallisation study, similar to that shown above in Table 9, again using MeOH, THF and acetone, the results are reported in Table 11 below.

15 Table 11 Recrystallisation of Cipamfylline from various solvents<sup>a</sup>

entry	solvent	conc <sup>n</sup> (g/ml)	time to cool <sup>b</sup> to 20-25°C (min)	recovered yield (%)	polymorphic <sup>c</sup> form
1	MeOH	0.018	60	70	II
2	Acetone	0.004	40	64	II <sup>d</sup> + I
3	Acetone	0.004	~1 <sup>e</sup>	22	I
4	Acetone	0.004	~1 <sup>e</sup>	49	I
5	THF	0.017	~1 <sup>e</sup>	33	I + III
6	THF	0.017	60	58	I

notes: a General method: x g of BRL-61063 were suspended in y ml of the appropriate solvent and heated to reflux whereupon dissolution occurred. The solution was then cooled over the appropriate time and the product isolated by filtration.

20 b Time to cool from reflux to 20-25°C.

c Determined by IR Spectroscopy

d Predominantly form II, some form I.

e Crash cooling of solution with an ice bath.

These data (Table 11) show that slow crystallisation of BRL-61063 from MeOH (entry 1) provided product in polymorph form II. Polymorph form II was the predominant form obtained from slow cooling of an acetone solution of BRL-61063 (entry 2). Crash cooling of an identical solution (entry 3) gave BRL-61063 in exclusively form I. The fast cooling experiment was repeated and gave form I product (entry 4) confirming the original observation.

BRL-61063 was dissolved in THF and fast cooling led to isolation of material existing in polymorphic forms I and III (entry 5). Form I was exclusively obtained from slow cooling (entry 6).

These experiments therefore provide for another aspect of the present invention which is a process for producing Form I, which process comprises placing crude Cipamfylline in an organic solvent, dissolving the crude product by heating to about reflux temperature and then cooling to crystalize out the desired form.

For Form I, the preferred solvent is 1-propanol, acetone or THF, more preferably 1-propanol. For Form I, the reaction cooling time is determined by the minimum time to cool from reflux, or from the temperature at which dissolution of the crude product occurred in a solvent, i.e. from a minimum time to crash cooling a solution, which on a commercial scale is about 15 minutes. Preferably, the minimum cooling time is a realistic time period of about 50 - 70 minutes to what ever is desired, such as overnight (i.e. 8 to 12 hours). Preferably, the cooling time is about 60-70 minutes with a range to about 120 minutes to overnight if desired. The cooling temperature is preferably from about 0°C to about 25°C, preferably from about 15°C to about 25°C, more preferably from about 18°C to about 25 °C. Also, ethanol is an alternative solvent, but only if crash cooling is used. If Form II is desired than ethanol, or methanol, is useful if a long cooling time is used 9 (see table 9 or 11).

If THF is used as a solvent to produce Form I, than slow cooling is necessary, and if acetone is used, than fast cooling is necessary as well.

It is recognized that other combinations of solvents under suitable conditions may be used herein, these combinations could include admixture with water, or with other organic solvents, such as DMF, heptanes, MeCN, n-butanol, isopropanol, ethyl acetate, TBME, toluene, decalin, etc. All of these are included within the meaning of a modifications or improvements of the specifically exemplified embodiments herein. It is recognized that this is within the skilled artisans means to produce the optimal

solvent for use for recrystallization on a laboratory and commercial scale using the disclosures herein.

5 All publications, including but not limited to patents and patent applications, cited in this specification are herein incorporated by reference as if each individual publication were specifically and individually indicated to be incorporated by reference herein as though fully set forth.

10 The above description fully discloses the invention including preferred embodiments thereof. Modifications and improvements of the embodiments specifically disclosed herein are within the scope of the following claims. Without further elaboration, it is believed that one skilled in the art can, using the preceding description, utilize the present invention to its fullest extent. Therefore the Examples  
15 herein are to be construed as merely illustrative and not a limitation of the scope of the present invention in any way. The embodiments of the invention in which an exclusive property or privilege is claimed are defined as follows.

What is Claimed is:

1. A crystalline polymorph of 1,3-di-cyclopropylmethyl-8-amino xanthine that exhibits an X-ray powder diffraction pattern having characteristic peaks expressed in d spacing (Å) in decreasing intensity, at approximately 12.302, 7.702, 8.532, 4.289, and 2.854, and as expressed in Figure 1.
2. A crystalline polymorph of 1,3-di-cyclopropylmethyl-8-amino xanthine that exhibits an infrared absorption spectrum in potassium bromide having characteristic absorption bands expressed in reciprocal centimeters as described in Figure 20.
3. A crystalline polymorph of 1,3-di-cyclopropylmethyl-8-amino xanthine that that exhibits a single crystal X-ray crystallographic analysis with (a) crystal parameters that are approximately equal to the following:
 

15	Crystal shape (mm)	Flat needles
	Crystal dimensions	1.0 x 0.12 x 0.08 mm
	Crystal color	Colorless
	Space Group	P1 triclinic #2
	Temperature	295K
20	Cell Constants	a = 10.829 (2) Å
		b = 12.636(2) Å
		c = 5.105(3) Å
		alpha (α) = 99.48(4)
		beta (β) = 91.53(4)
25		gamma (γ) = 83.84(3)
	Volume	685.0(8) Å <sup>3</sup>
	Molecules/unit cell (Z)	4
	Density, (ρ) g/cm <sup>-3</sup>	1.354
	μ	7.362 cm <sup>-1</sup>
30	F(000)	292

the atomic positions of all atoms relative to the origin of the unit cell as represented in the tables of FIGURES 12 to 15.
4. A crystalline polymorph of 1,3-di-cyclopropylmethyl-8-amino xanthine that exhibits a Raman Spectroscopy pattern as expressed in Figure 4.
5. A crystalline polymorph of 1,3-di-cyclopropylmethyl-8-amino xanthine

that exhibits an X-ray powder diffraction pattern having characteristic peaks expressed in d spacing (Å) in decreasing intensity, at approximately 12.001, 6.702, 3.687, 3.773, and 7.345, and as expressed in Figure 2.

5 6. A crystalline polymorph of 1,3-di-cyclopropylmethyl-8-amino xanthine that exhibits an infrared absorption spectrum in potassium bromide having characteristic absorption bands expressed in reciprocal centimeters as described in Figure 21.

10 7. A crystalline polymorph of 1,3-di-cyclopropylmethyl-8-amino xanthine that exhibits a single crystal X-ray crystallographic analysis with crystal parameters that are approximately equal to the following:

Crystal Shape (mm): Rectangular blocks

Space Group P2<sub>1</sub>/c monoclinic #14

Cell Constants a = 12.227 (4) Å

15 b = 7.448(2) Å

c = 14.946 (8) Å

beta (β) = 97.95(4)

Volume 1348.1(9) Å<sup>3</sup>

Molecules/unit cell (Z) 4

20 ρ (calc) Density 1.356 g/cm<sup>-3</sup>

μ 0.896 cm<sup>-1</sup>

F(000) 584

25 8. A crystalline polymorph of 1,3-di-cyclopropylmethyl-8-amino xanthine that exhibits a Raman Spectroscopy pattern as expressed in Figure 5.

9. A crystalline polymorph of 1,3-di-cyclopropylmethyl-8-amino xanthine that exhibits an infrared absorption spectrum of a crystal having characteristic absorption bands expressed in reciprocal centimeters as described in Figures 18, 24 or 25.

30

10. A crystalline polymorph of 1,3-di-cyclopropylmethyl-8-amino xanthine that exhibits a single crystal X-ray crystallographic analysis with crystal parameters that are approximately equal to the following:

Crystal shape (mm) Flat needles

35 Space Group P1 triclinic #2

Cell Constants a = 10.210(3) Å

b = 13.753(2) Å

$$c = 4.942(31) \text{ \AA}$$

$$\alpha (\alpha) = 97.94(2)$$

$$\beta (\beta) = 97.95(4)$$


$$\gamma (\gamma) = 83.33(2)$$

5	Volume	677.1(5) $\text{\AA}^3$
	Molecules/unit cell (Z)	2
	Density, $\text{g/cm}^{-3}$	1.350

11. A crystalline polymorph of 1,3-di-cyclopropylmethyl-8-amino xanthine that  
 10 exhibits a Raman Spectroscopy pattern as expressed in Figure 6.
12. A pharmaceutical composition comprising an amount of a polymorph  
 according to any one of Claims 1 to 4, and a pharmaceutically acceptable carrier or  
 diluent.
- 15 13. A pharmaceutical composition comprising an amount of a polymorph  
 according to any one of Claims 5 to 8, and a pharmaceutically acceptable carrier or  
 diluent.
- 20 14. A pharmaceutical composition comprising an amount of a polymorph  
 according to any one of Claims 9 to 11, and a pharmaceutically acceptable carrier or  
 diluent.
- 25 15. A method of treating a PDE<sub>4</sub> mediated disease in a mammal in need thereof,  
 which method comprises administering to said mammal an effective amount of a  
 polymorph according to any one of Claims 1 to 4.
- 30 16. A method of treating a PDE<sub>4</sub> mediated disease in a mammal in need thereof,  
 which method comprises administering to said mammal an effective amount of a  
 polymorph according to any one of Claims 5 to 8.
- 35 17. A method of treating a PDE<sub>4</sub> mediated disease in a mammal in need thereof,  
 which method comprises administering to said mammal an effective amount of a  
 polymorph according to any one of Claims 9 to 11.



18. A method of treating a TNF mediated disease in a mammal in need thereof, which method comprises administering to said mammal an effective amount of a polymorph according to any one of Claims 1 to 4.
- 5 19. A method of treating a TNF mediated disease in a mammal in need thereof, which method comprises administering to said mammal an effective amount of a polymorph according to any one of Claims 5 to 8.
20. A method of treating a TNF mediated disease in a mammal in need thereof, which method comprises administering to said mammal an effective amount of a polymorph according to any one of Claims 9 to 11.
- 10 21. A process for producing a crystalline polymorph of 1,3-di-cyclopropylmethyl-8-amino xanthine, Form I, which process comprises
- 15 a) dissolving 1,3-di-cyclopropylmethyl-8-amino xanthine in 1-propanol; and  
b) cooling the solution to crystalize out of solution the desired polymorphic Form I.
22. The process according to Claim 21 wherein the 1-propanol is admixed with water.
- 20 23. The process according to Claim 21 wherein the cooling temperature is from about 0 to about 25° C.
24. The process according to Claim 23 wherein the crystalization time is from about 15 to about 120 minutes.
- 25 25. The process according to Claim 21 wherein the xanthine is dissolved by heating the 1-propanol to reflux conditions.
- 30 26. A process for producing a crystalline polymorph of 1,3-di-cyclopropylmethyl-8-amino xanthine, Form I, which process comprises
- a) dissolving 1,3-di-cyclopropylmethyl-8-amino xanthine in tetrahydrofuran or acetone; and
- b) cooling the solution to crystalize out of solution the desired polymorphic Form I.
- 35






FIG. 2

**TABLE 4**

Torsion Angle Tabulations for Forms II and IV

	Form II	Form IV
C7-N8-C10-C11	101.8(3)	74.6(3)
C9-N8-C10-C11	-84.6(3)	-99.5(3)
C5-N8-C10-C11	98.7(3)	91.7(3)
C7-N6-C14-C15	-80.2(3)	-85.1(3)
N8-C10-C11-C12	-77.5(3)	80.4(3)
N8-C10-C11-C13	-146.6(3)	149.8(3)
C10-C11-C12-C13	-104.9(4)	-107.5(3)
N6-C14-C15-C16	-88.5(3)	89.4(3)
N6-C14-C15-C17	-158.3(3)	158.8(3)
C14-C15-C16-C17	-108.1(3)	-111.4(3)

**FIGURE 3**




FIG. 4




FIG. 5




FIG. 6




FIG. 7






FIG. 8





FIG. 9

FIG. 10







FIG. II

**TABLE OF BOND DISTANCES IN ANGSTROMS**

<u>Atom 1</u>	<u>Atom 2</u>	<u>Distance</u>	<u>Atom 1</u>	<u>Atom 2</u>	<u>Distance</u>
O5	C5	1.237(2)	C10	C11	1.493(3)
O7	C7	1.211(2)	C11	C12B	1.155(5)
N1	C2	1.344(2)	C11	C12A	1.481(8)
N1	C9	1.367(2)	C11	C13B	1.366(9)
N2	C2	1.355(2)	C11	C13A	1.292(5)
N3	C2	1.343(2)	C12B	C12A	1.287(9)
N3	C4	1.397(2)	C12B	C13B	1.50(1)
N6	C5	1.399(2)	C12B	C13B	1.597(8)
N6	C7	1.402(2)	C12A	C13B	0.55(2)
N6	C14	1.476(2)	C12A	C13A	1.55(1)
N8	C7	1.388(2)	C13B	C13A	1.16(1)
N8	C9	1.365(2)	C14	C15	1.492(3)
N8	C10	1.461(2)	C15	C16	1.453(3)
C4	C5	1.407(2)	C15	C17	1.490(3)
C4	C9	1.362(2)	C16	C17	1.501(4)

---

Numbers in parentheses are estimated standard deviations in the least significant digits.

**FIGURE 12**

### TABLE OF BOND ANGLES IN DEGREES

<u>Atom 1</u>	<u>Atom 2</u>	<u>Atom 3</u>	<u>Angle</u>	<u>Atom 1</u>	<u>Atom 2</u>	<u>Atom 3</u>	<u>Angle</u>
C2	N1	C9	102.5(1)	C10	C11	C12A	124.9(4)
C2	N3	C4	105.6(1)	C10	C11	C13B	121.6(5)
C5	N6	C7	126.1(1)	C10	C11	C13A	132.1(5)
C5	N6	C14	119.0(1)	C12B	C11	C12A	56.9(4)
C7	N6	C14	114.8(1)	C12B	C11	C13B	72.5(5)
C7	N8	C9	119.4(1)	C12B	C11	C13A	81.3(4)
C7	N8	C10	119.4(1)	C12A	C11	C13B	21.6(7)
C9	N8	C10	121.2(1)	C12A	C11	C13A	67.8(6)
N1	C2	N2	122.8(1)	C13B	C11	C13A	51.6(6)
N1	C2	N3	114.1(1)	C11	C12B	C12A	74.5(5)
N2	C2	N3	123.0(1)	C11	C12B	C13B	60.3(4)
N3	C4	C5	131.5(1)	C11	C12B	C13A	53.1(3)
N3	C4	C9	105.1(1)	C12A	C12B	C13B	20.9(7)
C5	C4	C9	123.3(1)	C12A	C12B	C13A	64.1(6)
O5	C5	N6	120.7(1)	C13B	C12B	C13A	43.8(5)
O5	C5	C4	126.9(1)	C11	C12A	C12B	48.7(4)
N6	C5	C4	112.4(1)	C11	C12A	C13B	67.(1)
O7	C7	N6	121.5(2)	C11	C12A	C13A	50.3(4)
O7	C7	N8	121.6(1)	C12B	C12A	C13B	102.(2)
N6	C7	N8	116.8(2)	C12B	C12A	C13A	67.7(5)
N1	C9	N8	125.4(1)	C13B	C12A	C13A	36.(2)
N1	C9	C4	112.7(2)	C11	C13B	C12B	47.2(4)
N8	C9	C4	121.9(1)	C11	C13B	C12A	91.(2)
N8	C10	C11	113.6(2)	C11	C13B	C13A	60.9(6)
C10	C11	C12B	146.4(4)	C12B	C13B	C12A	57.(1)
C12B	C13B	C13A	72.5(9)	C12A	C13A	C13B	16.2(7)
C12A	C13B	C13A	127.(2)	N6	C14	C15	111.7(2)
C11	C13A	C12B	45.6(3)	C14	C15	C16	122.2(2)
C11	C13A	C12A	61.9(4)	C14	C15	C17	119.2(2)
C11	C13A	C13B	67.5(5)	C16	C15	C17	61.3(2)
C12B	C13A	C12A	48.2(4)	C15	C16	C17	60.6(2)
C12B	C13A	C13B	63.6(6)	C15	C17	C16	58.1(1)

Numbers in parenthesis are estimated standard deviations in the least significant digits.

## FIGURE 13

**TABLE OF TORSION ANGLES IN DEGREES**

<u>Atom 1</u>	<u>Atom 2</u>	<u>Atom 3</u>	<u>Atom 4</u>	<u>Angle</u>
C9	N1	C2	N2	178.39(0.21)
C9	N1	C2	N3	0.00(0.63)
C2	N1	C9	N8	179.65(0.20)
C2	N1	C9	C4	0.07(0.22)
H1N2	N2	C2	N1	17.67(1.50)
H1N2	N2	C2	N3	-164.06(1.48)
H2N2	N2	C2	N1	165.33(2.43)
H2N2	N2	C2	N3	-16.40(2.45)
C4	N3	C2	N1	-0.04(0.22)
C4	N3	C2	N2	-178.45(0.21)
HN3	N3	C2	N1	-173.47(0.22)
HN3	N3	C2	N2	8.13(0.40)
C2	N3	C4	C5	-176.94(0.24)
C2	N3	C4	C9	0.09(0.25)
HN3	N3	C4	C5	-2.31(0.36)
HN3	N3	C4	C9	174.71(0.19)
C7	N6	C5	O5	178.56(0.21)
C7	N6	C5	C4	-1.17(0.31)
C14	N6	C5	O5	3.23(0.32)
C14	N6	C5	C4	-176.50(0.20)
C5	N6	C7	O7	179.08(0.22)
C5	N6	C7	N8	-0.03(0.30)
C14	N6	C7	O7	-5.42(0.32)
C14	N6	C7	N8	175.47(0.20)
C5	N6	C14	C15	97.41(0.27)
C7	N6	C14	C15	-78.43(0.27)
C9	N8	C7	O7	-178.90(0.21)
C9	N8	C7	N6	0.21(0.31)
C10	N8	C7	O7	2.31(0.33)
C10	N8	C7	N6	-178.58(0.19)
C7	N8	C9	N1	-178.60(0.20)
C7	N8	C9	C4	0.94(0.31)

**FIGURE 14**

**TABLE OF TORSION ANGLES IN DEGREES**

<u>Atom 1</u>	<u>Atom 2</u>	<u>Atom 3</u>	<u>Atom 4</u>	<u>Angle</u>
C10	N8	C9	N1	0.17(0.34)
C10	N8	C9	C4	179.71(0.20)
C7	N8	C10	C11	92.91(0.28)
C9	N8	C10	C11	-85.86(0.29)
N3	C4	C5	O5	-0.82(0.42)
N3	C4	C5	N6	178.89(0.22)
C9	C4	C5	O5	-177.38(0.22)
C9	C4	C5	N6	2.33(0.32)
N3	C4	C9	N1	-0.10(0.27)
N3	C4	C9	N8	-179.69(0.20)
C5	C4	C9	N1	177.23(0.20)
C5	C4	C9	N8	-2.36(0.34)
N8	C10	C11	C12B	18.14(1.01)
N8	C10	C11	C12A	-62.89(0.57)
N8	C10	C11	C13B	-88.53(0.62)
N8	C10	C11	C13A	-153.29(0.60)
C10	C11	C12B	C12A	-104.52(0.89)
C10	C11	C12B	C13B	-121.16(0.96)
C10	C11	C12B	C13A	-173.58(0.98)
C12A	C11	C12B	C13B	-16.64(0.63)
C12A	C11	C12B	C13A	-69.05(0.61)
C13B	C11	C12B	C12A	16.64(0.63)
C13B	C11	C12B	C13A	-52.42(0.66)
C13A	C11	C12B	C12A	69.05(0.61)
C13A	C11	C12B	C13B	52.42(0.66)
C10	C11	C12A	C12B	139.20(0.69)
C10	C11	C12A	C13B	-88.56(1.41)
C10	C11	C12A	C13A	-126.69(0.69)
C12B	C11	C12A	C13B	132.25(1.54)
C12B	C11	C12A	C13A	94.12(0.79)
C13B	C11	C12A	C12B	-132.25(1.54)
C13B	C11	C12A	C13A	-38.13(1.41)
C13A	C11	C12A	C12B	-94.12(0.79)
C13A	C11	C12A	C13B	38.13(1.41)
C10	C11	C13B	C12B	146.19(0.63)
C10	C11	C13B	C12A	105.66(1.27)
C10	C11	C13B	C13A	-121.12(0.76)

**FIGURE 14 (CONTINUED)**



**TABLE OF TORSION ANGLES IN DEGREES**

<u>Atom 1</u>	<u>Atom 2</u>	<u>Atom 3</u>	<u>Atom 4</u>	<u>Angle</u>
C12B	C11	C13B	C12A	-40.53(1.33)
C12B	C11	C13B	C13A	92.69(0.84)
C12A	C11	C13B	C12B	40.53(1.33)
C12A	C11	C13B	C13A	133.22(1.59)
C13A	C11	C13B	C12B	-92.69(0.84)
C13A	C11	C13B	C12A	-133.22(1.59)
C10	C11	C13A	C12B	175.21(0.72)
C10	C11	C13A	C12A	117.55(0.63)
C10	C11	C13A	C13B	100.66(0.71)
C12B	C11	C13A	C12A	-57.66(0.60)
C12B	C11	C13A	C13B	-74.55(0.70)
C12A	C11	C13A	C12B	57.66(0.60)
C12A	C11	C13A	C13B	-16.88(0.58)
C13B	C11	C13A	C12B	74.55(0.60)
C13B	C11	C13A	C12A	16.88(0.58)
C11	C12B	C12A	C13B	-44.29(1.28)
C11	C12B	C12A	C13A	-56.10(0.52)
C13B	C12B	C12A	C11	44.29(1.28)
C13B	C12B	C12A	C13A	-11.81(1.22)
C13A	C12B	C12A	C11	56.10(0.52)
C13A	C12B	C12A	C13B	-11.81(1.22)
C11	C12B	C13B	C12A	129.22(1.48)
C11	C12B	C13B	C13A	-66.21(0.66)
C12A	C12B	C13B	C11	-129.22(1.48)
C12A	C12B	C13B	C13A	164.57(1.56)
C13A	C12B	C13B	C11	66.21(0.66)
C13A	C12B	C13B	C12A	-164.57(1.56)
C11	C12B	C13A	C12A	89.52(0.65)
C11	C12B	C13A	C13B	83.48(0.69)
C12A	C12B	C13A	C11	-89.52(0.65)
C12A	C12B	C13A	C13B	-6.04(0.58)
C13B	C12B	C13A	C11	-83.48(0.69)
C13B	C12B	C13A	C12A	6.04(0.58)
C11	C12A	C13B	C12B	-34.66(0.89)
C11	C12A	C13B	C13A	-53.29(1.16)
C12B	C12A	C13B	C11	34.66(0.89)
C12B	C12A	C13B	C13A	-18.63(1.76)

**FIGURE 14 (CONTINUED)**

**TABLE OF TORSION ANGLES IN DEGREES**

<u>Atom 1</u>	<u>Atom 2</u>	<u>Atom 3</u>	<u>Atom 4</u>	<u>Angle</u>
C13A	C12A	C13B	C12B	18.63(1.76)
C11	C12A	C13A	C12B	-54.08(0.56)
C11	C12A	C13A	C13B	106.19(1.75)
C12B	C12A	C13A	C11	54.08(0.56)
C12B	C12A	C13A	C13B	160.27(1.86)
C13B	C12A	C13A	C11	-106.19(1.75)
C13B	C12A	C13A	C12B	-160.27(1.86)
C11	C13B	C13A	C12B	-50.23(0.48)
C11	C13B	C13A	C12A	-66.54(1.64)
C12B	C13B	C13A	C11	50.23(0.48)
C12B	C13B	C13A	C12A	-16.31(1.55)
C12A	C13B	C13A	C11	66.54(1.64)
C12A	C13B	C13A	C12B	16.31(1.55)
N6	C14	C15	C16	-160.25(0.31)
N6	C14	C15	C17	-87.61(0.35)
C14	C15	C16	C17	108.17(0.40)
C14	C15	C17	C16	-112.98(0.37)

**FIGURE 14 (CONTINUED)**

### Positional Parameters and Their Estimated Standard Deviations

<u>Atom</u>	<u>X</u>	<u>Y</u>	<u>Z</u>	<u>B(A<sup>2</sup>)</u>
O5	1.5599(1)	1.8918(1)	1.1475(3)	4.88(4)
O7	1.3047(2)	1.7197(1)	0.5279(3)	5.25(4)
N1	1.1341(2)	1.9527(1)	1.2713(4)	3.77(4)
N2	1.1397(2)	2.0771(2)	1.6721(4)	4.71(4)
N3	1.3206(2)	1.9967(1)	1.4356(4)	3.89(4)
N6	1.4311(2)	1.8063(2)	0.8378(4)	4.13(4)
N8	1.2113(2)	1.8305(1)	0.8786(4)	3.90(4)
C2	1.1968(2)	2.0099(2)	1.4663(4)	3.70(4)
C4	1.3420(2)	1.9242(2)	1.1994(4)	3.83(4)
C5	1.4528(2)	1.8769(2)	1.0720(5)	3.94(5)
C7	1.3146(2)	1.7809(2)	0.7346(5)	4.11(5)
C9	1.2273(2)	1.9003(2)	1.1082(4)	3.57(4)
C10	1.0876(2)	1.8054(2)	0.7843(5)	4.60(5)
C11	1.0417(3)	1.7161(3)	0.9008(9)	8.42(9)
C12B	1.0527(8)	1.6649(6)	1.069(2)	10.7(2)
C12A	1.1006(7)	1.6034(5)	0.863(2)	9.9(2)
C13B	1.066(1)	1.6107(5)	0.786(2)	11.4(3)
C13A	0.9638(6)	1.6475(8)	0.814(2)	12.2(3)
C14	1.5381(2)	1.7453(2)	0.6891(5)	5.12(6)
C15	1.5630(3)	1.6339(3)	0.7530(7)	7.89(9)
C16	1.6823(4)	1.5701(4)	0.7024(9)	11.2(1)
C17	1.6453(4)	1.6152(4)	0.9832(9)	10.9(1)

Anisotropically refined atoms are given in the form of the isotropic equivalent displacement parameter defined as:  $(4/3) * [a^2 * B(1,1) + b^2 * B(2,2) + c^2 * B(3,3) + ab(\cos \gamma) * B(1,2) + ac(\cos \beta) * B(1,3) + bc(\cos \alpha) * B(2,3)]$

## FIGURE 15




FIG. 16




FIG. 17





FIG. 18






FIG. 20








FIG. 21

**Fig. 22**

**FIG. 23**




FIG. 24





FIG. 25

FIG. 26






FIG. 27

**TABLE OF BOND DISTANCES IN ANGSTROMS**

<u>Atom 1</u>	<u>Atom 2</u>	<u>Distance</u>	<u>Atom 1</u>	<u>Atom 2</u>	<u>Distance</u>	<u>Atom 1</u>	<u>Atom 2</u>	<u>Distance</u>
O5	C5	1.243(2)	N6	C7	1.396(2)	C11	C12	1.480(4)
O7	C7	1.214(2)	N6	C14	1.477(2)	C11	C13	1.468(3)
N1	C2	1.335(2)	N8	C7	1.390(2)	C12	C13	1.457(3)
N1	C9	1.367(2)	N8	C9	1.362(2)	C14	C15	1.494(3)
N2	C2	1.351(2)	N8	C10	1.475(2)	C15	C16	1.478(4)
N3	C2	1.345(2)	C4	C5	1.412(2)	C15	C17	1.487(3)
N3	C4	1.391(2)	C4	C9	1.358(2)	C16	C17	1.467(3)
N6	C5	1.398(2)	C10	C11	1.494(3)			

Numbers in parentheses are estimated standard deviations in the least significant digits.

**FIGURE 28**



**TABLE OF BOND ANGLES IN DEGREES**

Atom 1	Atom 2	Atom 3	Angle	Atom 1	Atom 2	Atom 3	Angle
C2	N1	C9	103.0(1)	C10	C11	C12	118.9(2)
C2	N3	C4	105.8(1)	C10	C11	C13	120.6(2)
C5	N6	C7	126.3(1)	C12	C11	C13	59.2(2)
C5	N6	C14	117.7(1)	C11	C12	C13	60.0(2)
C7	N6	C14	115.9(1)	C11	C13	C12	60.8(2)
C7	N8	C9	119.7(1)	N6	C14	C15	112.3(2)
C7	N8	C10	117.6(1)	C14	C15	C16	121.2(2)
C9	N8	C10	122.4(1)	C14	C15	C17	118.3(2)
N1	C2	N2	124.2(2)	C16	C15	C17	59.3(2)
N1	C2	N3	113.7(1)	C15	C16	C17	60.6(2)
N2	C2	N3	122.1(2)	C15	C17	C16	60.0(2)
N3	C4	C5	131.3(2)				

Numbers in parentheses are estimated standard deviations in the least significant digits.

**FIGURE 29**

**TABLE OF TORSIONAL ANGLES IN DEGREES**

	Atom 1	Atom 2	Atom 3	Atom 4	Angle	Atom 1	Atom 2	Atom 3	Atom 4	Angle
C9	N1	C2	C2	N2	179.22(0.22)	N3	C4	C9	N8	-178.86(0.19)
C9	N1	C2	C2	N3	0.77(0.25)	C5	C4	C9	N1	176.60(0.20)
C2	N1	C9	C9	N8	178.50(0.21)	C5	C4	C9	N8	-2.61(0.34)
C2	N1	C9	C9	C4	-0.68(0.24)	N8	C10	C11	C12	80.44(0.32)
H1N2	N2	C2	C2	N1	167.56(2.15)	N8	C10	C11	C13	149.79(0.27)
H1N2	N2	C2	C2	N3	-14.11(2.17)	N8	C10	C11	HC11	4.32(2.94)
H2N2	N2	C2	C2	N1	11.84(1.96)	HC10	C10	C11	C12	-159.31(2.98)
H2N2	N2	C2	C2	N3	-169.83(1.93)	HC10	C10	C11	C13	-89.96(2.98)
C4	N3	C2	C2	N1	-0.59(0.26)	HC10	C10	C11	HC11	124.57(4.16)
C4	N3	C2	C2	N2	-179.07(0.21)	C10	C11	C12	C13	110.38(0.32)
HN3	N3	C2	C2	N1	-177.62(1.77)	C10	C11	C12	HC11	-147.35(1.63)
HN3	N3	C2	C2	N2	3.89(1.79)	C10	C11	C12	HC13	-1.59(0.50)
C2	N3	C4	C4	C5	-175.70(0.23)	C13	C11	C12	HC11	102.26(1.61)
C2	N3	C4	C4	C9	0.13(0.23)	C13	C11	C12	HC13	-111.98(0.40)
HN3	N3	C4	C4	C5	0.78(2.14)	HC11	C11	C12	C13	-102.26(1.61)
HN3	N3	C4	C4	C9	176.60(2.11)	HC11	C11	C12	HC13	145.76(1.64)
C7	N6	C5	C5	O5	178.11(0.21)	C10	C11	C13	C12	-107.50(0.33)
C7	N6	C5	C5	C4	-1.77(0.31)	C10	C11	C13	HC12	141.23(0.31)
C14	N6	C5	C5	O5	1.69(0.31)	C12	C11	C13	HC12	-111.28(0.38)
C14	N6	C5	C5	C4	-178.19(0.19)	HC11	C11	C13	C12	56.85(1.39)
C5	N6	C7	C7	O7	179.80(0.22)	HC1	C11	C13	HC12	-54.43(1.41)
C5	N6	C7	C7	N8	-0.20(0.32)	C10	C11	HC11	C12	92.91(2.68)

**FIGURE 30**

TABLE OF TORSIONAL ANGLES IN DEGREES

Atom 1	Atom 2	Atom 3	Atom 4	Angle	Atom 1	Atom 2	Atom 3	Atom 4	Angle
C14	N6	C7	O7	-3.72(0.32)	C13	C11	HC11	C12	-57.68(0.80)
C14	N6	C7	N8	176.29(0.19)	C11	C12	C13	HIC12	109.36(0.36)
C5	N6	C14	C15	91.67(0.25)	HC11	C12	C13	C11	-45.77(1.19)
C5	N6	C14	HIC14	-150.04(2.73)	HC11	C12	C13	HIC12	63.59(1.22)
C7	N6	C14	C15	-85.13(0.26)	HIC13	C12	C13	C11	108.50(0.41)
C7	N6	C14	HIC14	33.16(2.74)	HIC13	C12	C13	HIC12	-142.15(0.36)
C9	N8	C7	O7	-178.99(0.21)	C13	C12	HC11	C11	60.10(1.04)
C9	N8	C7	N6	1.01(0.30)	HIC13	C12	HC11	C11	-73.54(2.58)
C10	N8	C7	O7	6.73(0.32)	N6	C14	C15	C16	89.36(0.32)
C10	N8	C7	N6	-173.28(0.19)	N6	C14	C15	C17	158.79(0.25)
C7	N8	C9	N1	-178.77(0.21)	N6	C14	C15	HC15	-53.54(2.68)
C7	N8	C9	C4	0.33(0.32)	HIC14	C14	C15	C16	-26.61(2.79)
C10	N8	C9	N1	-4.78(0.34)	HIC14	C14	C15	C17	42.82(2.78)
C10	N8	C9	C4	174.32(0.21)	HIC14	C14	C15	HC15	-169.51(3.84)
C7	N8	C10	C11	74.61(0.27)	C14	C15	C16	C17	106.62(0.32)
C7	N8	C10	HIC10	-50.49(2.79)	HC15	C15	C16	C17	-104.94(2.34)
C9	N8	C10	C11	-99.51(0.26)	C14	C15	C17	C16	-111.35(0.32)
C9	N8	C10	HIC10	135.39(2.79)	C14	C15	C17	HIC16	139.79(0.30)
N3	C4	C5	O5	-1.55(0.40)	C16	C15	C17	HIC16	-108.85(0.37)
N3	C4	C5	N6	178.32(0.21)	HC15	C15	C17	C16	97.10(2.41)
C9	C4	C5	O5	-176.73(0.22)	HC15	C15	C17	HIC16	-11.75(2.43)
C9	C4	C5	N6	3.14(0.31)	C15	C16	C17	HIC16	110.17(0.40)
N3	C4	C9	N1	0.35(0.25)					

FIGURE 30(CONTINUED)

# **POSITIONAL PARAMETERS AND THEIR ESTIMATED STANDARD DEVIATIONS**

<u>ATOM</u>	<u>X</u>	<u>Y</u>	<u>Z</u>	<u>B(A2)</u>
O5	0.1193(2)	0.8847(1)	0.7643(3)	4.17(4)
O7	-0.0432(2)	0.7070(1)	-0.0448(3)	4.94(4)
N1	-0.3270(2)	0.9413(1)	0.4337(4)	3.61(4)
N2	-0.3813(2)	1.0649(2)	0.7969(5)	5.08(5)
N3	0.1646(2)	0.9868(1)	0.7668(4)	3.62(4)
N6	0.0374(2)	0.7967(1)	0.3570(4)	3.69(4)
N8	0.1894(2)	0.8182(1)	0.1688(4)	3.63(4)
C2	0.2944(2)	0.9987(2)	0.6689(5)	3.68(5)
C4	0.1072(2)	0.9147(2)	0.5811(5)	3.48(5)
C5	0.0236(2)	0.8679(2)	0.5850(5)	3.42(5)
C7	0.0633(2)	0.7697(2)	0.1476(5)	3.83(5)
C9	0.2085(2)	0.8891(2)	0.3845(5)	3.33(4)
C10	0.3002(2)	0.7832(2)	-0.0323(5)	4.21(5)
C11	-0.3407(3)	0.6883(2)	0.0279(7)	5.89(7)
C12	-0.4282(4)	0.6908(3)	0.2439(8)	7.09(9)
C13	-0.4789(3)	0.6647(2)	-0.0445(7)	6.82(8)
C14	0.1687(2)	0.7401(2)	0.3404(5)	4.33(5)
C15	0.1807(3)	0.6467(2)	0.4687(6)	5.81(7)
C16	0.1415(3)	0.5538(2)	0.3060(9)	7.6(1)
C17	0.2830(3)	0.5663(2)	0.3858(8)	6.86(9)

Anisotropically refined atoms are given in the form of the isotropic equivalent displacement parameter defined as:  $(4/3) * [a^2 * B(1,1) + b^2 * B(2,2) + c^2 * B(3,3) + ab(\cos \gamma) * B(1,2) + ac(\cos \beta) * B(1,3) + bc(\cos \alpha) * B(2,3)]$

## **FIGURE 31**



**TABLE OF BOND DISTANCES IN ANGSTROMS**

<u>Atom 1</u>	<u>Atom 2</u>	<u>Distance</u>	<u>Atom 1</u>	<u>Atom 2</u>	<u>Distance</u>
O5	C5	1.251(3)	N8	C10	1.485(3)
O7	C7	1.216(3)	C4	C5	1.386(3)
N1	C2	1.352(3)	C4	C9	1.368(3)
N1	C9	1.351(3)	C10	C11	1.494(4)
N2	C2	1.344(3)	C11	C12	1.493(4)
N3	C2	1.340(3)	C11	C13	1.509(4)
N3	C4	1.394(3)	C12	C13	1.513(5)
N6	C5	1.402(3)	C14	C15	1.496(4)
N6	C7	1.403(3)	C15	C16	1.498(4)
N6	C14	1.474(3)	C15	C17	1.491(4)
N8	C7	1.375(3)	C16	C17	1.497(4)
N8	C9	1.375(3)			

---

Numbers in parentheses are estimated standard deviations in the least significant digits.

**FIGURE 33**

**TABLE OF BOND ANGLES IN DEGREES**

<u>Atom 1</u>	<u>Atom 2</u>	<u>Atom 3</u>	<u>Angle</u>	<u>Atom 1</u>	<u>Atom 2</u>	<u>Atom 3</u>	<u>Angle</u>
C2	N1	C9	102.9(2)	O7	C7	N8	122.2(2)
C2	N3	C4	106.5(2)	N6	C7	N8	117.1(2)
C5	N6	C7	125.4(2)	N1	C9	N8	125.6(2)
C5	N6	C14	119.4(2)	N1	C9	C4	113.2(2)
C7	N6	C14	115.3(2)	N8	C9	C4	121.2(2)
C7	N8	C9	119.7(2)	N8	C10	C11	113.2(2)
C7	N8	C10	119.0(2)	C10	C11	C12	118.9(3)
C9	N8	C10	121.0(2)	C10	C11	C13	115.7(3)
N1	C2	N2	122.6(2)	C12	C11	C13	60.5(2)
N1	C2	N3	113.2(2)	C11	C12	C13	60.3(2)
N2	C2	N3	124.2(2)	C11	C13	C12	59.2(2)
N3	C4	C5	132.3(2)	N6	C14	C15	111.5(2)
N3	C4	C9	104.3(2)	C14	C15	C16	119.3(2)
C5	C4	C9	123.4(2)	C14	C15	C17	118.6(3)
O5	C5	N6	120.1(2)	C16	C15	C17	60.1(2)
O5	C5	C4	126.7(2)	C15	C16	C17	59.7(2)
N6	C5	C4	113.2(2)	C15	C17	C16	60.2(2)
O7	C7	N6	120.7(2)				

Numbers in parentheses are estimated standard deviations in the least significant digits.

**FIGURE 34**

**TABLE OF TORSION ANGLES IN DEGREES**

<u>Atom 1</u>	<u>Atom 2</u>	<u>Atom 3</u>	<u>Atom 4</u>	<u>Angle</u>
C9	N1	C2	N2	178.05(0.24)
C9	N1	C2	N3	0.08(0.30)
C2	N1	C9	N8	-177.92(0.24)
C2	N1	C9	C4	0.10(0.28)
H1N2	N2	C2	N1	23.12(2.03)
H1N2	N2	C2	N3	-159.14(2.01)
H2N2	N2	C2	N1	168.86(2.37)
H2N2	N2	C2	N3	-13.40(2.39)
C4	N3	C2	N1	-0.23(0.28)
C4	N3	C2	N2	-178.15(0.24)
HN3	N3	C2	N1	-179.38(2.06)
HN3	N3	C2	N2	2.70(2.09)
C2	N3	C4	C5	178.30(0.28)
C2	N3	C4	C9	0.27(0.26)
HN3	N3	C4	C5	-2.56(2.13)
HN3	N3	C4	C9	179.41(2.09)
C7	N6	C5	O5	-176.21(0.23)
C7	N6	C5	C4	4.06(0.35)
C14	N6	C5	O5	5.06(0.35)
C14	N6	C5	C4	-174.67(0.22)
C5	N6	C7	O7	178.07(0.24)
C5	N6	C7	N8	-1.50(0.37)
C14	N6	C7	O7	-3.15(0.36)
C14	N6	C7	N8	177.28(0.22)
C5	N6	C14	C15	98.71(0.28)
C5	N6	C14	H1C14	-23.62(1.66)
C5	N6	C14	H2C14	-139.30(1.34)
C7	N6	C14	C15	-80.15(0.29)
C7	N6	C14	H1C14	157.52(1.64)
C7	N6	C14	H2C14	41.84(1.36)
C9	N8	C7	O7	178.13(0.25)
C9	N8	C7	N6	-2.30(0.35)
C10	N8	C7	O7	-8.17(0.38)
C10	N8	C7	N6	171.39(0.22)
C7	N8	C9	N1	-178.88(0.24)
C7	N8	C9	C4	3.26(0.36)

**FIGURE 35**



**TABLE OF TORSION ANGLES IN DEGREES**

<u>Atom 1</u>	<u>Atom 2</u>	<u>Atom 3</u>	<u>Atom 4</u>	<u>Angle</u>
C10	N8	C9	N1	7.55(0.38)
C10	N8	C9	C4	-170.32(0.24)
C7	N8	C10	C11	101.83(0.28)
C7	N8	C10	H1C10	-138.74(1.37)
C7	N8	C10	H2C10	-20.54(1.49)
C9	N8	C10	C11	-84.56(0.30)
C9	N8	C10	H1C10	34.87(1.39)
C9	N8	C10	H2C10	153.07(1.47)
N3	C4	C5	O5	-0.50(0.47)
N3	C4	C5	N6	179.21(0.25)
C9	C4	C5	O5	177.22(0.25)
C9	C4	C5	N6	-3.08(0.36)
N3	C4	C9	N1	-0.23(0.29)
N3	C4	C9	N8	177.88(0.22)
C5	C4	C9	N1	-178.49(0.23)
C5	C4	C9	N8	-0.38(0.40)
N8	C10	C11	C12	-77.46(0.37)
N8	C10	C11	C13	-146.45(0.28)
N8	C10	C11	HC11	69.33(2.00)
H1C10	C10	C11	C12	165.55(1.46)
H1C10	C10	C11	C13	96.55(1.46)
H1C10	C10	C11	HC11	-47.66(2.46)
H2C10	C10	C11	C12	38.83(1.63)
H2C10	C10	C11	C13	-30.17(1.63)
H2C10	C10	C11	HC11	-174.38(2.54)
C10	C11	C12	C13	-104.89(0.35)
C10	C11	C12	H1C12	-3.01(2.32)
C10	C11	C12	H2C12	145.37(2.57)
C13	C11	C12	H1C12	101.87(2.29)
C13	C11	C12	H2C12	-109.74(2.58)
HC11	C11	C12	C13	106.38(1.89)
HC11	C11	C12	H1C12	-151.74(2.94)
HC11	C11	C12	H2C12	-3.35(3.20)
C10	C11	C13	C12	110.08(0.32)
C10	C11	C13	H1C13	-142.62(3.05)
C10	C11	C13	H2C13	-12.37(0.72)

**FIGURE 35 (CONTINUED)**

**TABLE OF TORSION ANGLES IN DEGREES**

<u>Atom 1</u>	<u>Atom 2</u>	<u>Atom 3</u>	<u>Atom 4</u>	<u>Angle</u>
C12	C11	C13	H1C13	107.30(3.06)
C12	C11	C13	H2C13	-122.45(0.65)
HC11	C11	C13	C12	-104.01(1.90)
HC11	C11	C13	H1C13	3.29(3.59)
HC11	C11	C13	H2C13	133.54(1.94)
C11	C12	C13	H1C13	-95.14(3.19)
C11	C12	C13	H2C13	130.82(0.53)
H1C12	C12	C13	C11	-106.46(2.08)
H1C12	C12	C13	H1C13	158.40(3.79)
H1C12	C12	C13	H2C13	24.36(2.14)
H2C12	C12	C13	C11	104.58(2.65)
H2C12	C12	C13	H1C13	9.43(4.15)
H2C12	C12	C13	H2C13	-124.61(2.67)
N6	C14	C15	C16	-88.54(0.33)
N6	C14	C15	C17	-158.33(0.26)
N6	C14	C15	HC15	63.31(1.86)
H1C14	C14	C15	C16	31.45(1.66)
H1C14	C14	C15	C17	-38.35(1.65)
H1C14	C14	C15	HC15	-176.71(2.45)
H2C14	C14	C15	C16	153.51(1.42)
H2C14	C14	C15	C17	83.71(1.44)
H2C14	C14	C15	HC15	-54.65(2.33)
C14	C15	C16	C17	-108.05(0.32)
C14	C15	C16	H1C16	-0.20(1.73)
C14	C15	C16	H2C16	144.46(2.42)
C17	C15	C16	H1C16	107.85(1.72)
C17	C15	C16	H2C16	-107.49(2.43)
HC15	C15	C16	C17	103.34(2.05)
HC15	C15	C16	H1C16	-148.81(2.65)
HC15	C15	C16	H2C16	-4.15(3.19)
C14	C15	C17	C16	109.24(0.32)
C14	C15	C17	H1C17	-143.46(2.06)
C14	C15	C17	H2C17	-0.28(2.06)
C16	C15	C17	H1C17	107.30(2.08)
C16	C15	C17	H2C17	-109.52(2.04)

**FIGURE 35 (CONTINUED)**

**TABLE OF TORSION ANGLES IN DEGREES**

<u>Atom 1</u>	<u>Atom 2</u>	<u>Atom 3</u>	<u>Atom 4</u>	<u>Angle</u>
HC15	C15	C17	C16	-114.19(2.00)
HC15	C15	C17	H1C17	-6.89(2.88)
HC15	C15	C17	H2C17	136.29(2.83)
C15	C16	C17	H1C17	-108.70(2.12)
C15	C16	C17	H2C17	107.42(2.08)
H1C16	C16	C17	C15	-100.24(1.88)
H1C16	C16	C17	H1C17	151.06(2.81)
H1C16	C16	C17	H2C17	7.18(2.80)
H2C16	C16	C17	C15	111.79(2.55)
H2C16	C16	C17	H1C17	3.09(3.32)
H2C16	C16	C17	H2C17	-140.79(3.27)

**FIGURE 35 (CONTINUED)**

# **POSITIONAL PARAMETERS AND THEIR ESTIMATED STANDARD DEVIATIONS**

<u>ATOM</u>	<u>X</u>	<u>Y</u>	<u>Z</u>	<u>B(A<sup>2</sup>)</u>
O5	0.9075(2)	-0.3990(2)	0.8878(1)	3.22(4)
O7	0.7135(2)	0.1280(3)	.08696(1)	3.93(5)
N1	0.9202(2)	-0.0215(3)	1.1348(1)	2.60(5)
N2	1.0398(2)	-0.1997(3)	1.2364(2)	3.35(5)
N3	0.9771(2)	-0.2857(3)	1.0851(1)	2.85(5)
N6	0.8070(2)	-0.1371(3)	0.8743(1)	2.61(5)
N8	0.8128(2)	0.0729(3)	0.9941(2)	2.61(5)
C2	0.9803(2)	-0.1720(4)	1.1549(2)	2.58(5)
C4	0.9096(2)	-0.2061(3)	1.0131(2)	2.44(5)
C5	0.8785(2)	-0.2590(4)	0.9243(2)	2.53(5)
C7	0.7738(2)	0.0287(4)	0.9061(2)	2.86(6)
C9	0.8781(2)	-0.0468(3)	1.0473(2)	2.33(5)
C10	0.7932(2)	0.2569(4)	1.0268(2)	3.20(6)
C11	0.7010(3)	0.2660(5)	1.0827(2)	4.22(7)
C12	0.5848(3)	0.2621(6)	1.0363(3)	6.2(1)
C13	0.6342(3)	0.4370(5)	1.0743(3)	7.0(1)
C14	0.7592(2)	-0.1827(4)	0.7812(2)	3.04(6)
C15	0.6443(2)	-0.2544(4)	0.7773(2)	3.73(7)
C16	0.6275(3)	-0.4518(5)	0.7891(3)	5.49(9)
C17	0.5985(3)	0.3664(5)	0.6983(3)	5.36(9)

Anisotropically refined atoms are given in the form of the isotropic equivalent displacement parameter defined as:  $(4/3) * [a^2*B(1,1) + b^2*B(2,2) + c^2*B(3,3) + ab(\cos \gamma) * B(1,2) + ac(\cos \beta) * B(1,3) + bc(\cos \alpha) * B(2,3)]$

## **FIGURE 36**

## INTERNATIONAL SEARCH REPORT

International application No.  
PCT/US98/22451

<b>A. CLASSIFICATION OF SUBJECT MATTER</b> IPC(6) :C07D 473/16; A61K 31/52 US CL :544/272; 514/263 According to International Patent Classification (IPC) or to both national classification and IPC		
<b>B. FIELDS SEARCHED</b> Minimum documentation searched (classification system followed by classification symbols) U.S. : 544/272; 514/263 Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched Electronic data base consulted during the international search (name of data base and, where practicable, search terms used) CAS Online		
<b>C. DOCUMENTS CONSIDERED TO BE RELEVANT</b>		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X -- A	WO 92/05176 A1 (BEECHAM GROUP PLC) 02 April 1992, page 26, lines 10-21.	1-20 ----- 21-26
X,P -- A,P	US 5,734,051 A (SPICER ET AL.) 31 March 1998, Example 9.	1-20 ----- 21-26
X -- A	WO 92/05175 A1 (BEECHAM GROUP PLC) 02 April 1992, page 40, lines 20-36.	1-20 ----- 21-26
<input type="checkbox"/> Further documents are listed in the continuation of Box C. <input type="checkbox"/> See patent family annex.		
* Special categories of cited documents: *A* document defining the general state of the art which is not considered to be of particular relevance *B* earlier document published on or after the international filing date *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) *O* document referring to an oral disclosure, use, exhibition or other means *P* document published prior to the international filing date but later than the priority date claimed	*T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principles or theory underlying the invention *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art *Z* document member of the same patent family	
Date of the actual completion of the international search 14 JANUARY 1999		Date of mailing of the international search report 29 JAN 1999
Name and mailing address of the ISA/US Commissioner of Patents and Trademarks Box PCT Washington, D.C. 20231 Facsimile No. (703) 305-3230		Authorized officer MARK L. BERCH <i>for</i> Telephone No. (703) 308-1235